



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 28/02, 24/32 // (C04B 28/02, 24:02, 24:32, 24:38), 103:40, 103:44	A1	(11) International Publication Number: WO 98/24734 (43) International Publication Date: 11 June 1998 (11.06.98)
(21) International Application Number: PCT/EP97/06945 (22) International Filing Date: 28 November 1997 (28.11.97) (30) Priority Data: 8/340448 6 December 1996 (06.12.96) JP (71) Applicant (for all designated States except US): MBT HOLD- ING AG [CH/CH]; Vulkanstrasse 110, CH-8048 Zürich (CH). (72) Inventors; and (75) Inventors/Applicants (for US only): MATSUO, Shigemi [JP/JP]; 786-1, Hamanogou, Chigasaki-chi, Kanagawa-ken (JP). NAGAMINE, Hidenori [JP/JP]; 2722, Hagizono, Chigasaki-chi, Kanagawa-ken (JP). OTA, Akira [JP/JP]; 1-5-42, Enzo, Chigasaki-chi, Kanagawa-ken (JP).		(81) Designated States: AU, CA, CN, DE, GB, SG, US. Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: FLOWABILITY ADDITIVE (57) Abstract <p>A cement pumpability-enhancing additive which confers good pumpability on cementitious compositions such as concrete consists essentially of (a) polyethylene glycol; (b) diethylene glycol monobutyl ether and/or a derivative thereof; (c) polysaccharide; and (d) a thickening polymer selected from the group consisting of polyacrylic acid derivatives, polyacrylic amide derivatives, cellulose ethers, polyphenyl ethers and polyalkylene glycol fatty acid esters; the weight solids proportions of (a), (b), (c), and (d) in the additive being respectively 5-55 %, 10-80 %, 1-20 % and 1-20 %. The additive is preferably used with a cement dispersing agent.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

FLOWABILITY ADDITIVE

5 The present invention relates to a method of improving the pumpability of cementitious compositions and to a cement additive which is intended to improve the workability of cementitious compositions for pump application.

10 Pump application is a way of conveying cement compositions such as cement paste, mortar, and concrete to a desired place by means of a pump. In the building of modern large-scale concrete structures, efficient conveyance of large quantities of concrete is achieved by employing a high-capacity pump and a large-diameter pipe or branched pipes, the latter permitting concrete to be cast over a large area at one time. While this method is acceptable for conventional concrete, it is not acceptable for the high strength, high-flow
15 concrete used in high-rise concrete buildings in urban areas, and which concrete exhibits special properties such as high strength and self-filling. If it is attempted to pump such concrete by the method hereinabove described, it will lose flowability during its conveyance, the degree of loss depending on mix proportions, environment and on-site conditions. The carrying out of the process and the quality of the final concrete are thereby
20 compromised.

 Several means have been proposed to address this problem, involving increasing the amount of powder or fine aggregate in a concrete mix, decreasing the amount of mixing water, or adding a thickening agent. These means, however, have the disadvantage of
25 increasing the concrete viscosity, raising the pumping pressure, and reducing the durability of the cured concrete (because of the presence of a higher proportion of powder). Such disadvantages sometimes hinder site execution and quality control, and hence the abovementioned means are not a satisfactory solution at the present time.

30 The use of pumpability admixtures has been suggested, one such admixture containing as essential ingredients polyethylene glycol and polycarboxylic acid-based dispersing agent. Unfortunately, this dispersing agent increases the concrete viscosity or cannot prevent the decrease of flowability completely after pumping.

There is therefore a demand for cement additive which permits smooth pump application of concrete, while ensuring good flowability and pumpability, without causing increase in viscosity.

5 In British Patent 2,297,086 there is disclosed a pumping aid which is a combination of polyethylene glycol and diethylene glycol monobutyl ether (butyl "Carbitol" (trade mark) or a derivative thereof). An optional component in this pumping aid was a polysaccharide.

10 This pumping aid provided a considerable advance in the art, but it was found that in certain difficult circumstances its performance was not adequate. Such circumstances included the considerable change in fluidity just after a mixing, or the fluctuations caused by such factors as change in the mix proportions of the composition being pumped, fluctuations in aggregate quality, or an increase in pumping pressure in a desire to reduce time.

15 It has now been found that it is possible substantially to overcome these problems and provide good pumpability and flowability for such concretes while retaining their good properties. The invention therefore provides a cement pumpability-enhancing additive which consists essentially of

- 20 (a) polyethylene glycol;
 - (b) diethylene glycol monobutyl ether and/or a derivative thereof;
 - (c) polysaccharide; and
 - (d) a thickening polymer selected from the group consisting of polyacrylic acid derivatives, polyacrylic amide derivatives, cellulose ethers, polyphenyl ethers and polyalkylene glycol fatty acid esters;
- 25 the weight solids proportions of (a), (b), (c), and (d) in the additive being respectively 5-55%, 10-80%, 1-20% and 1-20%.

The invention additionally provides a method of improving the pumpability of a cementitious composition by the incorporation therein prior to pumping of an additive as
30 hereinabove defined.

Diethylene glycol monobutylether (hereinafter "DGME") is a well-known material and is commercially available, for example, as butyl "Carbitol" (trade mark). The derivative

used in the present invention is preferably an adduct of DGME with 1-2 mol of propylene oxide. It is preferred to have present at least some DGME, and the preferred material is a mixture of DGME and the abovementioned adduct.

5 The polyethylene glycol used in the present invention is preferably one which has an average molecular weight (weight-average) of from 4,000 to 150,000. It is preferably present in the proportion of from 5-50%.

10 The polysaccharide used in the present invention is preferably one or more selected from curdlan, sugar alcohol, xanthan gum, guar gum, welan gum and β -1,3-glucan.

15 The thickening polymers for use in this invention may be selected from a wide range of suitable materials. Preferred examples include polyacrylic acid derivatives, polyacrylamide derivatives, cellulose ethers, polyalkylene glycol fatty acid esters and alkylphenyl ethers. In the case of polyacrylic acid derivatives, polyacrylamide derivative and cellulose ethers, they should be such that the viscosity of 1 wt. % aqueous solution is from 1,000-1,000,000 cP (20°C). In the case of polyalkylene glycol fatty acid esters and alkylphenyl ethers, the viscosity of 10 wt. % aqueous solution of these is preferably 10-500 cP (20°C). It is possible and permissible to use more than one such thickening polymer.

20 The cement pumpability-enhancing additive according to the present invention should be used in an amount adequate to achieve good pumpability with retention of properties. This will vary depending on the cement composition to which it is added. Usually the amount ranges from 0.05 to 5.0, preferably from 0.05 to 2, wt% (in terms of solids in the cement additive) for the amount of cement contained in the cement composition. It is not specifically limited so long as there is enough to impart desired flowability and pumpability to the cement composition for pump application.

25 The cement additive according to the present invention should preferably be used in combination with a cement dispersing agent. This may be selected from any of the commercial-available cement dispersing agents, such as a polycarboxylic acid, aminosulfonic acid, a naphthalenesulfonic acid-formalin condensate, a melamine sulfonic acid-formalin condensate, ligninsulfonic acid, and a hydroxycarboxylic acid, and metal salts

thereof (including alkali metal salts and alkaline earth metal salts). In this particular embodiment, the cement dispersing agent should be present in an amount up to 3% (by weight solids on cement). In this case, the total proportion of additive + cement dispersing agent should not exceed 5% by weight solids based on cement.

5

The abovementioned DGME/DGME derivative, polyethylene glycol, polysaccharide, thickening polymer and dispersing agent should preferably be used blended as a single component; however, they may also be used as two or more components.

10

The cement pumpability-enhancing additive according to the present invention may be used in combination with other additives, such as air-entraining agents, drying shrinkage reducing agents, high-early strengthening agents, setting accelerators, setting retarders, defoaming agents, rust inhibitors and accelerating agents. Such additives perform their normal functions and are used in art-recognised quantities.

15

Cementitious compositions to which the additives of this invention have been added exhibit a combination of good pumpability and good viscosity. The compositions flow well and are easy to apply. In an especially valuable embodiment of the invention, the high-strength, high-flow concretes used nowadays for construction, which have not been easy to pump using conventional technology, can be made readily pumpable with little or no loss of properties by means of this invention. A particular feature of the invention is the ability of the compositions according to the invention to minimise changes in fluidity under the circumstances hereinabove described. The invention therefore also provides a method for applying a cementitious composition by pumping, wherein there is first added to the composition a pumpability-enhancing additive as hereinabove described, and the cementitious composition is then pumped. The invention further provides a pumpable cementitious composition comprising a cementitious composition and a pumpability-enhancing additive as hereinabove described.

20

25

30

The present invention will now be further explained with reference to the following non-limiting examples which demonstrate the application of the cement additive to mortar and concrete.

Examples**Materials used**a) Fine aggregate:

5 Oi river system land sand (specific gravity =2.59, fineness modulus=2.72: hereinafter described as "land sand".)

Ako, Hyougo prefecture, crushed sand (specific gravity=2.56, fineness modulus=2.93: hereinafter described as "crushed sand".)

10 Kisarazu, Chiba prefecture, pit sand (specific gravity=2.63, fineness modulus=2.41: hereinafter described as "pit sand".)

b) Coarse aggregate:

Ome sandstone crushed stone (specific gravity=2.65, maximum particle diameter=20mm)

c) Cement:

15 Ordinary portland cement ("OPC") manufactured by Chichibu Onoda Cement Corporation, (specific gravity=3.16)

Low heat portland cement ("LHC") manufactured by Nihon Cement Co., Ltd. (specific gravity=3.20)

20 Usage of ordinary portland cement manufactured by Nihon Cement Co., Ltd. and fly-ash manufactured by Denpatsu Coaltech Co., Ltd. in a weight ratio of 4 to 1 ("FAC") (specific gravity=2.97)

d) Thickening polymer

Polyacrylamide derivative ("Sumiflock" (trade mark) FA-200 manufactured by Sumitomo Chemical Co., Ltd. ("PAA")

Cellulose ether (SFCA-2000 manufactured by Shin-Etsu Chemical Co., Ltd. ("CLE")

25 Polyalkylene glycol fatty acid ester (Ionet (trade mark) DO-1000 manufactured by Sanyo Kasei Kogyo Co., Ltd. ("PAG")

Alkylphenyl ether ("Nonipol" (trade mark) 100 manufactured by Sanyo Kasei Kogyo Co., Ltd. ("APE")

e) DGME derivative:

30 Butyl "Carbitol" ("BCR"), tert-butyl "Carbitol" ("TBC"), adduct of butyl "Carbitol" with 1 mol of propylene glycol ("BP1"), adduct of butyl "Carbitol" with 2 mol of propylene glycol ("BP2")

f) Polyethylene glycol derivatives:

Polyethylene glycol (average molecular weight 4000, hereinafter referred to as PG-04)

Polyethylene glycol (average molecular weight 10000, hereinafter referred to as PG-10)

Polyethylene glycol (average molecular weight 20000, hereinafter referred to as PG-20)

- 5 Polyethylene glycol (average molecular weight 150000, hereinafter referred to as PG-150)

g) Polysaccharide

Curdlan (hereinafter referred to as CA)

Sugar alcohol "Sorbit" (trade mark) PO-30 manufactured by Towa Kasei Kogyo Co., Ltd., hereinafter referred to as PO)

- 10 Xanthan gum (hereinafter referred to as XG)

Guar gum (hereinafter referred to as GG)

h) Cement dispersing agent:

Polycarboxylate "Rheobuild" (trade mark) SP-8N manufactured by NMB Ltd., hereinafter referred to as SP-8N)

- 15 Formalin high condensates of naphthlenesulfonate "Rheobuild" SP-9N manufactured by NMB Ltd., hereinafter referred to as SP-9N)

Formaldehyde high condensate of melamine sulfonate "Rheobuild" NL-4000 manufactured by NMB Ltd., hereinafter referred to as NL-40)

- 20 Mixture of lignosulfonate and oxycarboxylate ("Pozzolith" (trade mark) No. 70 by NMB Ltd., hereinafter referred to as PZ-70)

1) Mortar and concrete: mix proportion, preparation and materials

I-I) Mortar

- 25 An evaluation test is carried out using mortar of the mix proportion shown in Table 1. Each material is measured so that the volume of the mix is 30 litres, and all the materials are placed into a pan-type enforced mixer with a nominal capacity of 50 litres and mixed for 120 seconds to prepare the mortar. For the mix proportion shown in Table 1 are determined water-cement ratio, sand-cement ratio, unit water content, unit cement content and unit fine-aggregate content on the basis of the mix proportion of high flow concrete which exhibits 60±5 cm in the slump flow in which a unit cement volume is about 550 kg/m³.
- 30 Additionally, the air content of the mortar is in the range of 1.5±0.5 vol%.

1-2) Concrete

An evaluation test is carried out using concrete of the mix proportion No. 1 and 2 shown in Table 2. Each material is measured so that the volume of the mix is 4 m³ and all the materials are placed into an enforced twin-shaft mixer with a capacity of 4 m³ and mixed for 60 seconds to prepare concrete. Additionally, the slump, slump flow, and air content of the mix proportion No. 1 are 25.5 cm, 58.0-71.0 cm, and 1.0-2.0 % respectively, and those of the mix proportion No. 2 are 18.5-19.5 cm, 28.0-34.0 cm, and 4.0-5.0 % respectively.

Table 1

Mix No.	Water/cement ratio (%)	Sand/cement ratio	Cement	Fine aggregate
1	30.0	1.30	OPC	land sand
2			OPC	crushed sand
3			OPC	pit sand
4			LHC	land sand
5			FAC	land sand

Table 2

Mix No.	Water/cement ratio (%)	Percent fine aggregate (%)	Unit contents (kg/m ³)		Cement	Fine aggregate
			Water	Cement		
1-A	30.0	44.8	170	567	OPC	land sand
1-B					OPC	pit sand
1-C					LHC	pit sand
2	55.0	49.0	170	309	OPC	land sand

i) Sample:

In Table 3 are shown the types and the mixing ratio of thickening polymers, DGME derivatives, polyethylene glycols and polysaccharides of sample used in examples and comparative examples.

Table 3

Type of sample	Components and their mixing ration (wt. %)							
	DGME		Polyethylene glycol		Polysaccharide		Thickening polymer	
	Type	Ratio	Type	Ratio	Type	Ratio	Type	Ratio
A	BCR	40	PG-20	40	CA	15	CLE	5
B	TBC	40	PG-20	40	CA	15	CLE	5
C	BC1	40	PG-20	40	CA	15	CLE	5
D	BC2	40	PG-20	40	CA	15	CLE	5
E	BCR	25	PG-04	55	CA	15	CLE	5
F	BCR	30	PG-10	50	CA	15	CLE	5
G	BCR	75	PG-150	5	CA	15	CLE	5
H	BCR	40	PG-20	40	CA	5	CLE	5
I	BCR	40	PG-20	40	XG	5	CLE	5
J	BCR	40	PG-20	40	GG	5	CLE	5
K	BCR	45	PG-20	45	CA	8	PAA	2
L	BCR	40	PG-20	40	CA	10	PAG	10
M	BCR	35	PG-20	35	CA	10	AFE	20
O	-	-	PG-20	100	-	-	-	-
P	-	-	PG-150	100	-	-	-	-
Q	-	-	-	-	-	-	PAA	100
R	-	-	-	-	-	-	CLE	100
S	BCR	49	-	-	CA	48	CLE	3
T	BCR	49	PG-20	48	-	-	CLE	3
U	BCR	40	PG-20	40	CA	20	-	-

2) Test method of mortar and concrete

5 2-1) Static pressure test for mortar

Using the mixed mortar samples shown in Table 1, there are measured the flow (Fp1) of mortar intermittently added with a constant pressure and the flow (F0) of the same mortar preserved at a standing condition for the same period of time. From this can be calculated the mortar flow ratio (Fp1/F0) to evaluate the effect that the static pressure condition exerts on the fluidity of mortar. These test results are shown in Table 4.

a) Application of pressure: The mortar sample is placed in a test container specified by "Pressure Bleeding Test Method" in "Guide for Pump Application of Concrete (draft)" prescribed by the Japan Society of Civil Engineers, and is pressurised so that the pressure reaches 50 kgf/cm^2 in 5 seconds. After maintaining this for 10 seconds, the pressure is relieved in 5 seconds. After repeating 30 cycles of this operation, the mortar flow is measured.

b) Mortar flow: The flow cone is used which is specified by "Method for Physical Test of Cement" in JIS R-5201. After pulling up the flow cone filled with mortar, a stopped mortar spread is measured.

2-2) Pumping test of mortar

Using the mixed mortar samples shown in Table 1, there are measured the flow (F_{p2}) of mortar after pumping at a constant discharge volume and at a constant pumping time in each case and the flow (F_0) of the mortar preserved at a standing condition for the same period of time as the pumping time, thereby being calculated mortar flow ratio (F_{p2}/F_0) to evaluate the effect that the pumping condition exerts on the fluidity of mortar.

a) Pumping condition:

1) Pump: Mortar pump DM15 manufactured by Shin-Meiwa Kogyo Co., Ltd.

2) Pipe length: Flexible hose (2.5cm x 5m)

10 3) Discharge volume: 6.0 liters/min.

4) Pumping time: 10 min.

5) Environmental temperature: 20°C

b) Mortar flow: Measured as in 2-1 above

15 2-3) Pumping-test method of concrete

Using concrete adjusted to the mix proportion shown in Table 2, there are measured the slump flow of concrete after pumping at a constant discharge volume and at a constant pumping time using a concrete pump, and the slump flow of concrete preserved at a standing condition for the same period of time as the pumping time, thereby being evaluated the effect that the pumping exerts on the fluidity of concrete.

q) Slump flow: According to "Method for Test of Concrete Slump Flow (draft)" prescribed by the Japan Society of Civil Engineers.

b) Air-entrainment property: According to JIS A 1128

c) Pumping condition:

25 1) Pumper: Model PY 110-25

2) Pipe length: Horizontal length 50 m (5 inch steel pipe)

3) Discharge volume: 30 m³/hr.

4) Environmental temperature: 20°C

3) Test results:

30 3-1) Mortar

In Table 4 are shown the results of the static pressure test and the pumping test. From Table 4 are ascertained the following effects in case of using the additive for cement composition in the invention for mortar.

Table 4

	Additive for cement composition		Cement dispersing Agent		Cement	Fine aggregate	Mortar flow (mm)			Static pressure test	Pumping test
	Type	Amount Used as solids cX%)	Type	Amount Used (as product content) (CX%)			Standing condition F0	After pressing FP1	After pumping FP2		
Ex.1 A		0.20	SP-8N	1.0	OPC	land sand	241	244	239	1.01	0.99
Ex.2 B		0.20	SP-8N	1.0	OPC	land sand	242	242	237	1.00	0.98
Ex.3 C		0.20	SP-8N	1.0	OPC	land sand	240	238	233	0.99	0.97
Ex.4 D		0.20	SP-8N	1.0	OPC	land sand	240	240	233	1.00	0.97
Ex.5 E		0.35	SP-8N	1.0	OPC	land sand	248	243	233	0.98	0.94
Ex.6 F		0.25	SP-8N	1.0	OPC	land sand	243	241	233	0.99	0.96
Ex.7 G		0.10	SP-8N	1.0	OPC	land sand	239	232	220	0.97	0.92
Ex.8 H		0.20	SP-8N	1.0	OPC	land sand	237	235	232	0.99	0.98
Ex.9 I		0.20	SP-8N	1.0	OPC	land sand	239	237	237	0.99	0.99
Ex.10 J		0.20	SP-8N	1.0	OPC	land sand	239	237	237	0.08	0.99
Ex.11 K		0.20	SP-8N	1.0	OPC	land sand	240	240	235	1.00	0.98
Ex.12 L		0.20	SP-8N	1.0	OPC	land sand	241	243	241	1.01	1.00
Ex.13 M		0.20	SP-8N	1.0	OPC	land sand	237	230	223	0.97	0.94
Ex.14 A		0.20	SP-9N	1.7	OPC	land sand	241	239	222	0.99	0.92
Ex.15 A		0.20	NL-40 PZ-70	2.0 250	OPC	land sand	235	230	214	0.98	0.91
Ex.16 L		0.20	SP-9N	1.7	OPC	land sand	239	237	222	0.99	0.93
Ex.17 L		0.20	NL-40 PZ-70	2.0 250	OPC	land sand	233	226	210	0.97	0.90
Ex.18 A		0.20	SP-8N	0.9	LHC	land sand	250	252	249	1.01	1.00
Ex.19 A		0.20	SP-8N	0.9	OPC+F A	land sand	245	246	242	1.00	0.99
Ex.20 A		0.20	SP-8N	1.0	OPC	crushed sand	249	247	244	0.99	0.98
Ex.21 A		0.20	SP-8N	1.0	OPC	pit sand	239	237	229	0.99	0.96

Table 4 (Cont'd)

	Additive for cement composition		Cement dispersing Agent		Cement	Fine aggregate	Mortar flow (mm)			Static pressure test	Pumping test	
	Type	Amount Used as solids (Cx%)	Type	Amount Used (as product content) (Cx%)			Standing condition F0	After pressing FP1	After pumping FP2		Flow ratio FP1/F0	Flow ratio FP2/F0 ¹⁾
Comparative ex. 1	O	0.10	SP-8N	1.0	OPC	land sand	241	227	200	0.94	0.83	1.08
Comparative ex. 2	P	0.10	SP-8N	1.0	OPC	land sand	237	223	199	0.94	0.84	1.06
Comparative ex. 3	Q	0.005	SP-8N	1.0	OPC	land sand	241	227	202	0.94	0.84	1.16
Comparative ex. 4	R	0.01	SP-8N	1.0	OPC	land sand	242	225	198	0.93	0.82	1.27
Comparative ex. 5	S	0.20	SP-8N	1.0	OPC	land sand	239	217	208	0.91	0.87	1.05
Comparative ex. 6	T	0.15	SP-8N	1.0	OPC	land sand	237	228	220	0.96	0.93	0.99
Comparative ex. 7	U	0.20	SP-8N	1.0	OPC	land sand	241	239	234	0.99	0.97	0.88
Comparative ex. 8	V	0.20	SP-8N	1.0	OPC	land sand	238	214	202	0.90	0.85	1.03
Comparative ex. 9	-	0.20	SP-8N	1.0	OPC	land sand	234	217	189	0.93	0.81	1.03
Comparative ex. 10	-	0.20	SP-9N	1.7	OPC	land sand	239	221	191	0.93	0.80	1.25
Comparative ex. 11	-	0.20	NL-40	2.0	OPC	land sand	229	206	164	0.90	0.72	1.38
		0.20	PZ-70	250.0 ²⁾								
Comparative ex. 12	U		SP-8N	0.9	LHC	land sand	268	263	248	0.98	0.93	0.89
Comparative ex. 13	U	0.20	SP-8N	0.8	LHC	land sand	245	233	218	0.95	0.89	0.95
Comparative ex. 14	U	0.20	SP-9N	1.0	OPC+FA	land sand	260	247	237	0.95	0.91	0.94
Comparative ex. 15	U	0.20	SP-8N	1.0	OPC	crushed sand	259	251	243	0.97	0.94	0.95
Comparative ex. 16	U		SP-8N	1.0	OPC	land sand	232	218	211	0.94	0.91	0.99
Comparative ex. 17	U	0.20	SP-9N	1.1	OPC	land sand	248	238	231	0.96	0.93	0.99

¹⁾ Pumping pressure: kgf/cm²²⁾ ml/C = 100 kg

The examples 1-13 are according to the invention.

- For comparison, it is shown that the comparative examples 1 and 2 are those to which polyethylene glycol and cement dispersing agent are added, the comparative examples 3 and 4 are those to which thickening polymer and cement dispersing agent are added, the comparative example 5 are those to which DGME derivative, polysaccharide, thickening polymer and cement dispersing agent are added, the comparative example 6 are those to which DGME derivative, polyethylene glycol, thickening polymer and cement dispersing agent are added, the comparative example 7 are those to which DGME derivative, polyethylene glycol, polysaccharide and cement dispersing agent are added, the comparative example 8 are those to which polyethylene glycol, polysaccharide, thickening polymer and cement dispersing agent are added, and the comparative examples 9-11 are those to which cement dispersing agent only are added.
- 15 The flow ratios of mortar in the static pressure condition and the pumping condition in the examples 1-13 are larger than those in the comparative examples 1-11 so that the decrease of fluidity is small and the pumping pressure is also small. Consequently, the pumpability of mortar using the additive in the invention shows a good performance in all cases.
- 20 The examples 14-17 show the cases in which the samples A or L of the invention and cement dispersing agents are used, and in which the type of the cement dispersing agent is varied. For comparison, it is shown that the comparative examples 9-11 are those to which cement dispersing agents only are added. The flow ratios of mortar on the static pressure condition and pumping condition in the examples 14-17 are larger than those in the comparative examples 9-11, therefore, it can be understood that the decrease of fluidity is small and the pumping pressure is also small. Consequently, it is ascertained that the pumpability of mortar using the additive of the invention shows a good performance even if the type of cement dispersing agent is changed.
- 25
- 30 The examples 1, 18 and 19 show the cases in which the sample A in the invention and a cement dispersing agent are used, and in which the type of cement is varied. For comparison, it is shown that the comparative examples 7, 12, 13 and 14 are the cases in which the sample U and the cement dispersing agent are used, and in which the type of

5 cement is varied. The fluidity change and pumping pressure of mortar on the static pressure condition and pumping condition in the examples 1, 18 and 19 are smaller than those in the comparative examples, and the pumpability of mortar employing the additive in the invention is good even if the type of cement is changed. On the contrary, the comparative
10 example 7, in which the fluidity change before and after pumping and the pumping pressure are also small, shows good pumpability. However, the comparative examples 12 and 14 show the tendency that the fluidity change just after a mixing and before and after pumping and the pumping pressure increase. Further, as shown in the comparative example 13, in the case when the added amount of the cement dispersing agent is decreased and the fluidity just
15 after the mixing is made identical with that of the examples, it is shown in that the fluidity change before and after pumping and the increase of pumping pressure tend to be accelerated.

The examples 1, 20 and 21 show the cases in which the sample A in the invention and a
20 cement dispersing agent are used, and in which the type of fine aggregates is varied. For comparison, it is shown that the comparative examples 7, 15, 16 and 17 are the cases in which the sample U and the cement dispersing agent are used, and in which the type of fine aggregates is varied. The fluidity change and pumping pressure of mortar on the static pressure condition and pumping condition in examples 1, 20 and 21 are smaller than those
25 in the comparative examples, and the pumpability of mortar using the additive of the invention is good even if the type of fine aggregates is changed. On the contrary, the comparative example 7, in which the fluidity change before and after pumping and the pumping pressure are also small, shows good pumpability, however, the tendency is shown that in the comparative example 15 the fluidity change just after mixing and before and after
30 pumping and the pumping pressure increase, and that in the comparative example 16, the fluidity just after mixing decreases and the fluidity change before and after pumping and the pumping pressure increase. Further, as shown in the comparative example 17, in the case where the added amount of the cement dispersing agent is increased and the fluidity just after the mixing is made identical with that of the examples, it is shown that the fluidity change before and the increase after pumping and the increase of the pumping pressure tend to be inhibited, however, its pumpability of mortar is inferior to that of mortar in which the additive of the invention is used.

3-2) Concrete test

5 In Table 5 are shown the results of the pumping test. From Table 5 are ascertained the following effects in the case of using the additive for cement composition in the invention for concrete.

10 The examples 22, 23, 27 and 28 show the cases in which the additives for cement composition of the invention are used. For comparison, it is shown that the comparative examples 21 and 22 are those adding cement dispersing agents only. The decreased amount of the slump flow before and after pumping, or of the slump in the examples 22, 23, 27 and 28 is 1.0-1.5 cm and is smaller compared to that in the comparative examples 21 and 22, showing that the pumpability of concrete using the additive in the invention is good.

15 The examples 22, 24 and 25 show the cases in which the sample A of the invention and a cement dispersing agent are used, while the types of cement or fine aggregate are varied. For comparison, it is shown that the comparative examples 18, 19 and 20 are the cases in which the sample U and the cement dispersing agent are used, while the types of cement or fine aggregate are varied. The decreased amount of the slump flow before and after pumping in
20 the examples 22, 24 and 25 is as small as 0.5-1.5 cm and the pumpability of concrete using the additive in the invention is good even if the types of cement or fine aggregate are changed. On the contrary, the comparative example 18, in which the decreased amount of the slump flow before and after pumping is as small as 1.5 cm, shows good pumpability, however, in the comparative examples 19 and 20 the decreased amount of the slump flow
25 just before and after pumping is as large as 6.0 cm and 4.0 cm respectively, and the change of the slump flow at the standing condition is also large compared to that of the examples.

Table 5

	Mix No.	Additive for cement composition		Cement		Cement	Fine aggregate	Measurement item	Time course	
		Type	Amount Used (as solids) (Cx%)	Type	Amount Used (as product content) (Cx%)				Standing condition	After pumping
Example 22	1	A	0.20	SP-8N	1.80	OPC	land sand	Slump flow(cm) Air content (%)	61.0 1.6	60.0 1.6
Example 23	1	K	0.20	SP-8N	1.80	OPC	land sand	Slump flow(cm) Air content (%)	61.5 1.5	60.5 1.3
Example 24	1	A	0.20	SP-8N	1.80	OPC	pit sand	Slump flow(cm) Air content (%)	63.0 1.3	61.5 1.3
Example 25	1	A	0.20	SP-8N	1.30	LHC	pit sand	Slump flow(cm) Air content (%)	64.0 1.0	63.5 1.2
Example 26	2	A	0.20	PZ-70	250ml/C=100kg	OPC	land sand	Slump flow(cm) Air content (%)	19.5 4.1	18.0 3.9
Example 27	2	L	0.10	PZ-79	250ml/C=100kg	OPC	land sand	Slump flow(cm) Air content (%)	18.5 4.5	17.5 4.2
Example 28	2	M	0.10	PZ-70	250ml/C=100kg	OPC	land sand	Slump flow(cm) Air content (%)	19.0 4.7	17.5 4.1
Comparative ex. 18	1	U	0.20	SP-8N	1.80	OPC	land sand	Slump flow(cm) Air content (%)	63.0 1.6	61.5 1.6
Comparative ex. 19	1	U	0.20	SP-8N	1.80	OPC	pit sand	Slump flow(cm) Air content (%)	58.0 1.6	52.0 1.6
Comparative ex. 20	1	U	0.20	SP-8N	1.30	LHC	pit sand	Slump flow(cm) Air content (%)	71.0 1.0	67.0 1.1
Comparative ex. 21	1	-	-	SP-8N	1.80	OPC	land sand	Slump flow(cm) Air content (%)	60.0 1.4	51.0 1.4
Comparative ex. 22	2	-	-	PZ-70	250ml/C=100kg	OPC	land sand	Slump flow(cm) Air content (%)	18.5 4.4	10.0 3.9

Consequently, use of the pumping additive according to the invention alleviates or removes entirely conventional problems, such as a considerable change of the fluidity just after mixing or before and after pumping, and an increase of pressure at a time of pumping, due to a difference in a mix proportion of cement composition or in a material used, and due to a
5 fluctuation of aggregate's grain or surface water. Thus, it becomes possible to prepare high-quality concrete that is extremely good in pumpability and flowability.

Claims:

1. A cement pumpability-enhancing additive which consists essentially of
 - (a) polyethylene glycol;
 - (b) diethylene glycol monobutyl ether and/or a derivative thereof;
 - (c) polysaccharide; and
 - (d) a thickening polymer selected from the group consisting of polyacrylic acid derivatives, polyacrylic amide derivatives, cellulose ethers, polyphenyl ethers and polyalkylene glycol fatty acid esters;the weight solids proportions of (a), (b), (c), and (d) in the additive being respectively 5-55%, 10-80%, 1-20% and 1-20%.
2. A cement pumpability-enhancing additive according to claim 1, wherein, when a derivative of diethylene glycol monobutyl ether is used, it is an adduct of diethylene glycol monobutyl ether with 1-2 mol of propylene oxide.
3. A cement pumpability-enhancing additive according to claim 1 or claim 2, wherein both diethylene glycol monobutyl ether and an adduct of diethylene glycol monobutyl ether with 1-2 mol of propylene oxide are used.
4. A cement pumpability-enhancing additive according to any one of claims 1-3, wherein the polysaccharide is selected from one or more of the group consisting of curdlan, sugar alcohol, xanthan gum, guar gum, welan gum and β -1,3-glucan.
5. A cement pumpability-enhancing additive according to any one of claims 1-4, wherein, when the thickening polymer is selected from polyacrylic acid derivatives, polyacrylamide derivatives and cellulose ethers, it is selected such that the viscosity of a 1 wt. % aqueous solution thereof is from 1,000-1,000,000 cP (20°C), and when it is selected from polyalkylene glycol fatty acid esters and alkylphenyl ethers, the viscosity of a 10 wt. % aqueous solution of these is from 10-500 cP (20°C).
6. A method of improving the pumpability of a cementitious composition by the incorporation therein prior to pumping of an additive according to claim 1.

7. A method of improving the pumpability of a cementitious composition according to claim 6, wherein there is additionally added to the cementitious composition a cement dispersing agent, this being present to the amount of 3% maximum solids by weight of cement.
- 5
8. A method of improving the pumpability of a cementitious composition according to claim 6 or claim 7, wherein the additive is added at a rate of from 0.05-5% by weight additive solids of cement, with the proviso that, when there is also present a cement dispersing agent, the combined proportion of the additive and the cement
- 10 dispersing agent (solids by weight of cement) shall not exceed 5% .
9. A method of improving the pumpability of a cementitious composition according to claim 7 or claim 8, wherein the cement dispersing agent is selected from at least one of a polycarboxylic acid, aminosulfonic acid, a naphthalenesulfonic acid-formalin
- 15 condensate, a melamine sulfonic acid-formalin condensate, ligninsulfonic acid, and a hydroxycarboxylic acid, and metal salts thereof (including alkali metal salts and alkaline earth metal salts).

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/06945

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C04B28/02 C04B24/32 /((C04B28/02,24:02,24:32,24:38),
C04B103:40,103:44

According to International Patent Classification(IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	GB 2 297 086 A (SANDOZ LTD) 24 July 1996 cited in the application see page 2, line 1 - page 3, line 1 ---	1-4,6-9
Y	CHEMICAL ABSTRACTS, vol. 104, no. 22, 2 June 1986 Columbus, Ohio, US; abstract no. 191910v, XP000061225 see abstract & JP 60 251 159 A (DAICEL CHEMICAL INDUSTRIES LTD) ---	1-4,6-9
A	US 4 126 009 A (E.A.TOMIC) 21 November 1978 see claims --- -/--	1,6

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

2 April 1998

Date of mailing of the international search report

09/04/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5618 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Theodoridou, E

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 97/06945

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 1 349 467 A (FEB) 3 April 1974 see the whole document -----	1,6,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 97/06945

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2297086 A	24-07-1996	JP 8198653 A DE 19602132 A FR 2729656 A US 5716447 A	06-08-1996 25-07-1996 26-07-1996 10-02-1998
US 4126009 A	21-11-1978	AU 524788 B AU 3950778 A CA 1142556 A DE 2835287 A DE 2857543 C DK 392178 A FR 2440487 A FR 2455691 A GB 2003851 A,B GB 2063847 A,B GB 2065256 A,B IN 157596 A LU 80204 A NL 7809056 A	07-10-1982 13-03-1980 08-03-1983 22-03-1979 04-07-1985 07-03-1979 30-05-1980 28-11-1980 21-03-1979 10-06-1981 24-06-1981 03-05-1986 01-06-1979 08-03-1979
GB 1349467 A	03-04-1974	NONE	